



Pure polyurea elastomer for internal lining of GRP pipes

DESCRIPTION

Polyurea SPP is a 2 component polyurea elastomer for the internal lining of GRP pipes, where a very high resistance to impact and abrasion is required. This product can only be applied by 2-component spraying equipment.

APPLICATION

- Industrial machinery and vehicle protection

PROPERTIES

- High adhesion and compatibility with most substrates (concrete, metal, GRP...).
- High resistance to abrasion / erosion and impact.
- Fast curing, allows for in-line processing without blisters.
- Available in different RAL colours.

TECHNICAL DATA

INFORMATION ON THE PRODUCT BEFORE APPLICATION

	Component A	Component B
Chemical description	Polyamine	Aromatic isocyanate pre-polymer
Physical state	Liquid	Liquid
Packaging	Metal container	Metal container
Note: Pigment is delivered in a third container. See Pigment Spray data sheet for specific details.	188 kg	208 kg
	18,8 kg	20,8 kg
Non-volatile content (%)	approx 100%	100%
Flash point	>100°C	>100°C
Colour	Dark yellow	Slightly yellow
Density	Temperature (°C)	Density (g/cm³)
	20	1.01
	60	0.98
Viscosity	Temperature (°C)	Viscosity (mPa.s)
Approximate	5	1100
Brookfield values	10	740
	20	425
	30	250
	40	140
	50	80
	60	60
Mixing ratio A/B	A=1, B=1,13 by weight A=1, B=1 by volume	
Density and viscosity of the mixture	Fast polymerization. See Pot life data	
Colour	Dark yellow, but component A is pigmented by addition of pigment paste (Pigment Spray) delivered with each kit of Polyurea SPP.	
Potlife	Gel time mixture A+B (20 g) 4 s at 25°C 3 s at 60°C	
Storage	Keep between 10° y 30°C.	
Use before	12 months after manufacture date, provided it is kept in its sealed container.	

Final state	Solid elastomeric membrane
Colour	Available Pigment Spray pastes are Gray RAL 7001, 7011. Tile red, Beige RAL 1001, blue RAL 5015. Other pastes under request.
Hardness (Shore)	50D 96A
Mechanical properties	Elongation at break: 270% Tensile strength: 17.2 MPa (UNE EN ISO 527-1/3) Tear strength: 100 N/mm (ISO 34-1 method B)
Adhesion strength	Surface Concrete Adhesion (MPa) 2.5
UV resistance	Good resistance to UV-induced degradation. Aromatic polyureas undergo change of colour under sunlight. This change does not affect its mechanical properties.
Abrasion resistance	Taber, CS10, 1000 c, 1 kg: 20 mg
Chemical resistance	Immersion test, 80°C, 7 days (0=worst, 5=best)

Chemical	Conditions	Result
Water	15d, 80°C	5
Salt water (saturation)	15d, 80°C	5
Xylene	7d, 80°C	2
Ethyl acetate	7d, 80°C	1
Isopropyl alcohol	7d, 80°C	0
Sodium hydroxide 50%	7d, 80°C	5
Hydrogen peroxide 33%	7d, 25°C	4
Sulfuric acid 10%	7d, 80°C	5
Sulfuric acid 30%	30d, 80°C	4
Bleach	7d, 80°C	4
Ammonia	7d, 80°C	5
Diesel	16d, 80°C	5
Hydrochloric acid 12M	7d, 80°C	0
37%		
Hydrochloric acid 6M	7d, 80°C	1
18%		
Hydrochloric acid 3M 9%	7d, 80°C	4
Hydrochloric acid 0.75M	7d, 80°C	5
2%		
Sodium hypochlorite	7d, 80°C	4
15%		
Engine oil	7d, 80°C	5
Crude petroleum	21d, 20°C	5
Sulfamic acid 85%	7d, 60°C	4
Oleic acid	7d, 80°C	0
Glycerine	7d, 80°C	5

SUPPORT REQUIREMENTS

Original paint must be removed and the surface must be clean and rust-free. Metal should be resistant to deformation by curing stress. Support temperature must be between 10°C and 40°C. At higher temperatures, additional measures to be advised by the manufacturer must be taken. Support moisture must be less than 4%

SUPPORT PREPARATION

Metal substrates must be thoroughly sanded and the final surface must be free of dust. A suitable adhesion-promoting primer must be used (e.g PU Primer) to prevent deformation, cracks or adhesion failure.

INFORMATION ON THE FINAL PRODUCT



KRYPTON CHEMICAL SL

C/ Martí i Franquès, 12 - Pol. Ind. les Tàpies
43890 - l'Hospitalet de l'Infant - Spain
Tel: +34 977 822 245 - Fax: +34 977 823 977
www.kryptonchemical.com - rayston@kryptonchemical.com

Latest update:

06/09/2022

Page:

1/2



Pure polyurea elastomer for internal lining of GRP pipes

MIXING

Stir and homogenise separately both components using suitable mixing equipment before being loaded into the machine. Add the required Pigment Spray to the A-component and stir before loading. Recirculate both components while heating up to the required application temperatures.

APPLICATION GUIDELINES

Polyurea SPP must be applied using a 2-component hot spraying equipment. Recommended temperatures are:

Component A: 65°C
Component B: 70°C

Pressure should be 130 bar.
During application, check layer thickness and curing speed.
Spray Polyurea SPP at 1-2 kg/m².

Wind speeds in excess of 25 km/h may result in excessive loss of exotherm and interfere with the mixing efficiency of the spray gun affecting polyurea surface texture, cure, and physical properties and will cause overspray issues.

Contact Krypton Chemical for more detailed technical information.

CURING TIME

Approximate hardness values are provided as reference only (2mm, polypropylene support, 20°C 50% rh)

Time	Hardness Shore D
5 min	35
45 min	43
6 hours	48
24 hours	50

REAPPLICATION

Usually, necessary thickness can be obtained in one single coat. If necessary, a second coat can be applied immediately afterwards. In any case, do not wait more than 2 hours for a second coat. If spraying over a previously applied epoxy primer, ensure the primer is completely cured (ca 8 hours)

RETURN TO SERVICE

Under most usual conditions (25°C, 50% rh), the membrane is able to resist light use in 1 hour. After 1 day, more than 90% of the final properties are reached.

TOOL CLEANING

Solvent use for machine component cleaning is discouraged. A cleaning plasticizer fluid like Rayston Fluid is suitable. Component B must be completely removed from all air-exposed parts and replaced with this cleaning fluid.

A maintenance work should be carried out regularly on the treated surfaces according to the intended use

FAQs

PROBLEM	QUESTION	CAUSE	SOLUTION
Product does not cure	AB ratio is correct?	Pressure differences	Check and correct machine operation
Bubbles or open pores	Porous support?	No primer	Apply suitable primer before Polyurea SPP Apply 1 kg/m ²
No hiding power	Horizontal?	Too little product Too little pigment	Ensure full A+pigment homogeneization
Colour change	Exposed to sunlight?	UV-reaction	Use a last coat in dark grey or red
Can it be			Not

applied
without
pigmentation?

recommended.
Polyurea SPP is always delivered with the pigment of choice. Use of pigment helps to obtain an uniform appearance

SAFETY

Component B contains isocyanates. Always follow the safety instructions in the Material Safety Data Sheet. As a general rule, a good ventilation and/or respiratory protection is needed (combined organic vapor filters+particles) along with protective clothing. This product must be used only for the applications here described. This product is intended for industrial and professional use. It is not suitable for DIY-type applications.

ENVIRONMENTAL PRECAUTIONS

Empty containers must be handled with the same precautions as if they were full. Treat empty containers as hazardous waste, and transfer them to an authorized waste manager. If the containers still have some material left, do not mix with other product with no knowledge of potential dangerous reactions. Component A and B may be mixed on a 1/1 ratio in order to get an inert material, but never do it in volumes larger than 5 litres in order to prevent a dangerous heat evolution.

OTHER INFORMATION

The information contained in this Technical Data Sheet, as well as our advice, both written as verbal or provided through testing, are based on our experience, and they do not constitute any product guarantee for the installer, who must consider them as simple information.

We recommend to study deeply all information provided before proceeding to the use or application of any of our products, and strongly advise to conduct tests "on-site" in order to determine their convenience for a specific project.

Our recommendations do not exempt of the obligation of installers to deeply study the right application method for these systems before use, as well as to conduct as many preliminary tests as possible should any doubt arise.

The application, use and processing of our products are beyond our control, and therefore under the exclusive responsibility of the installer. In consequence, the installer will be the only responsible of any damage derived from the partial or total in-observation of our indications, and in general, of the inappropriate use or application of these materials.

This Technical Data Sheet supersedes previous versions.