

# RAYSTON SPRAY D60 EPS

RAYSTON  
products



Sprayed, hot-applied modified polyurea membrane

## DESCRIPTION

Rayston Spray D60 EPS is a hard protective coating specially formulated for expanded polystyrene (EPS) foam. This product can only be applied by 2-component spraying equipment.

## APPLICATION

- Covering EPS foam and phenolic foam, as an impact protection
- Industrial machinery and vehicle protection
- Theming

## PROPERTIES

- Hard-flexible membrane
- Fast curing

## TECHNICAL DATA

### INFORMATION ON THE PRODUCT BEFORE APPLICATION

	Component A	Component B		
<b>Chemical description</b>	Polyol/Polyamine	Aromatic isocyanate prepolymer		
<b>Physical state</b>	Liquid	Liquid		
<b>Packaging</b>	Metal container 183 kg 23 kg	Metal container 213 kg 26.5 kg		
<b>Non-volatile content</b>	approx 100%	100%		
<b>Flash point</b>	>100°C	>100°C		
<b>Colour</b>	Slightly yellow	Brown		
<b>Density</b>	Temperature (°C) 25	Density (g/cm <sup>3</sup> ) 1.04	Temperature (°C) 25	Density (g/cm <sup>3</sup> ) 1,20
<b>Viscosity</b>	Temperature (°C) 25	Viscosity (mPa.s) 1800	Temperature (°C) 25	Viscosity (mPa.s) 1500
<b>Mixing ratio A/B</b>	A=1, B=1,15 by weight A=1, B=1 by volume			
<b>Density and viscosity of the mixture</b>	Fast polymerization. See Pot life data			
<b>Colour</b>	Clear yellow, but component A is pigmented by addition of pigment paste (Spray Pigment) delivered with each kit of Rayston Spray D60 EPS			
<b>Pot life</b>	Gel time mixture A+B (20 g): Approximate 7 seconds at 25°C 4-5 seconds at 60°C Tack-free: 15-20 seconds Time to sand: 10-15 minutes			
<b>Storage</b>	Keep between 10° y 30°C.			
<b>Use before</b>	12 months after manufacture date, provided it is kept in its sealed container.			

### INFORMATION ON THE FINAL PRODUCT

<b>Final state</b>	Solid elastomeric membrane
<b>Colour</b>	Available colours: light grey, dark grey, rust red, blue (may darken during storage and exposure to sunlight). Other colours under request.
<b>Hardness (Shore)</b>	65-70D (ISO 868)
<b>Mechanical properties</b>	Tensile strength: 25 MPa Elongation at break: 15% Tear strength: 83.3 N/mm

## UV resistance

Good resistance to UV-induced degradation. Aromatic polyureas undergo change of colour under sunlight. This change does not affect its mechanical properties. Additional UV protection can be achieved by application of an Impertrans or Colodur topcoat.

## SUPPORT REQUIREMENTS

To achieve a good penetration and bonding, support must be:

1. Compact and cohesive enough.
2. Free from cracks and fissures. If any, they must be previously repaired.
3. Clean and dry, free of dust, loose particles, oils, organic residues and paints.

Support temperature must be between 10°C and 40°C. At higher temperatures, additional measures to be advised by the manufacturer must be taken. Support moisture must be less than 4%.

## MIXING

Stir and homogenize separately both components using suitable mixing equipment before being loaded into the machine. Add the required Pigment Spray to the A-component and stir before loading. Recirculate both components while heating up to the required application temperatures.

## APPLICATION GUIDELINES

Rayston Spray D60 EPS must be applied using a 2-component hot spraying equipment.

Recommended temperatures are:

- Component A: 70°C
- Component B: 70°C

Pressure should be 130-150bar.

During application, check layer thickness and curing speed.

Spray Rayston Spray D60 EPS at 2 kg/m<sup>2</sup>. It is recommended to wait for a short period of time between applications to prevent exotherm and possible adherence issues.

Wind speeds more than 25 km/h may result in excessive loss of exotherm and interfere with the mixing efficiency of the spray gun affecting polyurea surface texture, cure, and physical properties and will cause overspray issues.

Contact Krypton Chemical for more detailed technical information.

## CURING TIME

Approximate hardness values are provided as reference only (1 mm, polypropylene support, 25°C 50% RH)

Time	Hardness (Shore D)
15 min	36
2 hours	50
7 hours	57
14 hours	60
24 hours	61

## REAPPLICATION

Needed thickness should be obtained in one single coat. A second coat is not recommended.



## KRYPTON CHEMICAL SL

C/ Martí i Franquès, 12 - Pol. Ind. les Tàpies  
43890 - l'Hospitalet de l'Infant - Spain  
Tel: +34 977 822 245 - Fax: +34 977 823 977

www.kryptonchemical.com - rayston@kryptonchemical.com

Latest update:

14/05/2024

Page:

1/2

# RAYSTON SPRAY D60 EPS

RAYSTON  
products



Sprayed, hot-applied modified polyurea membrane

## TOOL CLEANING

Solvent use for machine component cleaning is discouraged. A cleaning plasticizer fluid like Rayston Fluid is suitable. Component B must be completely removed from all air-exposed parts and replaced with this cleaning fluid.

## FAQs

PROBLEM	QUESTION	CAUSE	SOLUTION
The product does not cure	Is AB ratio correct?	Pressure differences	Check and correct machine operation
Bubbles or open pores	Porous support?	No primer unsuitable support	Apply a suitable primer before Rayston Spray D60 EPS
No hiding power	¿Horizontal?	Too little product Too little pigment	Apply 2 kg/m <sup>2</sup> Ensure full A + pigment homogenisation
Color change	Exposed to sunlight?	UV-reaction	Use a last coat in dark grey or red
	Can it be applied without pigmentation?		Use of pigment helps to obtain a uniform appearance.

## SAFETY

Component B contains isocyanates. Always follow the safety instructions in the Material Safety Data Sheet. As a rule, a good ventilation and/or respiratory protection is needed (combined organic vapour filters + particles) along with protective clothing. This product must be used only for the applications here described. This product is intended for industrial and professional use. It is not suitable for DIY-type applications.

## ENVIRONMENTAL PRECAUTIONS

Empty containers must be handled with the same precautions as if they were full. Treat empty containers as hazardous waste and transfer them to an authorized waste manager. If the containers still have some material left, do not mix with other product with no knowledge of potentially dangerous reactions. Component A and B may be mixed on a 1/1 ratio to get an inert material, but never do it in volumes larger than 5 litres to prevent a dangerous heat evolution.

## OTHER INFORMATION

The information contained in this Technical Data Sheet, as well as our advice, both written as verbal or provided through testing, are based on our experience, and they do not constitute any product guarantee for the installer, who must consider them as simple information.

We recommend studying deeply all information provided before proceeding to the use or application of any of our products, and strongly advise to conduct tests "on-site" to determine their convenience for a specific project.

Our recommendations do not exempt of the obligation of installers to deeply study the right application method for these systems before use, as well as to conduct as many preliminary tests as possible should any doubt arise.

The application, use and processing of our products are beyond our control, and therefore under the exclusive responsibility of the installer. In consequence, the installer will be the only responsible of any damage derived from the partial or total in-observation of our indications, and in general, of the inappropriate use or application of these materials.

***This Technical Data Sheet supersedes previous versions.***



### KRYPTON CHEMICAL SL

C/ Martí i Franquès, 12 - Pol. Ind. les Tàpies  
43890 - l'Hospitalet de l'Infant - Spain

Tel: +34 977 822 245 - Fax: +34 977 823 977

www.kryptonchemical.com - rayston@kryptonchemical.com

Latest update:

14/05/2024

Page:

2/2