



Bituminous membrane with fiberglass base

DESCRIPTION

Rayston Vel is an underlying sheet consisting of a glass fibre base coated with oxidised bitumen and sand finished on both surfaces. It is used to provide a controlled bond to the substrate in Impermax Strat system.

TECHNICAL DATA

INFORMATION ON THE FINAL PRODUCT

Packaging	Rolls 1 m width, 20 m length
Roll weight	34 kg
Base	Glass fibre
Base weight	60 g/m ²
Perforation diameter	25 mm (nominal)
Water vapour transmission rate	2710 (EN 1931, method B)
Storage	Keep at temperatures below 35°C, away from moisture and ignition sources. Use before 12 months after manufacturing date.

APPLICATION GUIDELINES

Glass fibre membranes should be installed according to the applicable standards. Usual pour/pull methods are advisable. Hot bitumen is poured in front of the roofing felt roll, which is then unrolled into the bitumen, spreading it to give a continuous coating. The membranes are applied with minimum 75 mm side and end laps.

SAFETY

See information provided in the relevant Material Safety Data Sheet.

ENVIRONMENT

Empty containers must be handled taking the same precautions as if they were full. Containers must be considered as hazardous waste, to be transferred to an authorized waste manager. If there is some residual product in the containers, do not mix it with other substances without checking for possible dangerous reactions.

OTHER INFORMATION

The information contained in this DATA SHEET, as well as our advice, both written as verbal or provided through testing, are based on our experience, and they do not constitute any product guarantee for the installer, who must consider them as simple information.

We recommend studying deeply all information provided before proceeding to the use or application of any of our products, and strongly advise to conduct tests "on-site" to determine their convenience for a specific project.

Our recommendations do not exempt of the obligation of installers to deeply study the right application method for these systems before use, as well as to conduct as many preliminary tests as possible should any doubt arise. The application, use and processing of our products are beyond our control, and therefore under the exclusive responsibility of the installer. In consequence, the installer will be the only responsible of any damage derived from the partial or total in-observation of our indications, and in general, of the inappropriate use or application of these materials.

This Data Sheet supersedes previous versions.